

## Material

**Rolyan® Polyform®**

## Temperature

1/16" (1.6mm) 150° to 160°F (65° to 70°C) water for 30 seconds  
1/8" (3.2mm) 150° to 160°F (65° to 70°C) water for 1 minute



## Stretch

**Minimum resistance**

## Time

1/16" (1.6mm) 1 minute of working time  
1/8" (3.2mm) 3 to 5 minutes of working time

**LATEX  
FREE**